

	Type	L #	Hits	Search Text	DBs
1	BRS	L1	242	(first adj ferroelectric adj2 (layer or film or section or portion or region))	US-PGPUB; USPAT
2	BRS	L2	1	1 near5 (defect or defects)	US-PGPUB; USPAT
3	BRS	L3	224	(second adj ferroelectric adj2 (layer or film or section or portion or region))	US-PGPUB; USPAT
4	BRS	L4	161	1 same 3	US-PGPUB; USPAT
5	BRS	L5	1	1 near15 (defect or defects)	US-PGPUB; USPAT
6	BRS	L6	8	1 same (defect or defects)	US-PGPUB; USPAT
7	BRS	L7	8	3 and 6	US-PGPUB; USPAT
8	BRS	L8	77	(first adj ferroelectric adj2 (layer or film or section or portion or region))	USOCR; EPO; JPO; DERWENT; IBM_TDB
9	BRS	L9	0	8 near15 (defect or defects)	USOCR; EPO; JPO; DERWENT; IBM_TDB